

ALPHA TALC[®] CT P FOR PAINTS

Product Properties

ALPHA TALC CT P is an industrial mineral with high whiteness, offering the option to enhance significantly several useful properties of paints. Due to special procedure, the natural lamellarity of the talc is kept. Addition of **ALPHA TALC CT P** to paints helps to save cost through reduction of organic solvents in paint formulation, what decreases VOC in these products. Application of this industrial mineral enhances important mechanical and thermal properties of paint formulations. Talc addition plays an important role in various paints applications: decorative paints, wall paints, wood lacquers, printing inks and industrial paints and coatings with improvement of the mud cracking resistance of the end-products.

EVERY BIG BAG SAVES YOUR MONEY

Key Benefits at a glance

- Expanded range of application in paints
- Excellent rheological properties
- High whiteness of powder
- Increasing mechanical stability
- Perfection of mud cracking resistance
- Reducing the permeability
- Development of weather resistance
- Enhancement of thermal properties



V2 / 2020-09-15 / OK

Alpha Calcit Füllstoff Gesellschaft mbH & Co. KG

D-50971 Köln Postfach 50 11 06
D-50997 Köln Otto-Hahn-Str. 9-11

Telefon: +49 2236 8914-0
Telefax: +49 2236 40644

Email: info@alpha-calcit.de
Internet: www.alpha-calcit.de



Die in unseren Informationen und Druckschriften angegebenen Werte sind Durchschnittswerte ohne Rechtsverbindlichkeit.
The data indicated on our data sheets and printed matters represent average values and are not legally binding.

ALPHA TALC[®] CT P FOR PAINTS

Introduction

Due to platy-shaped particles, **ALPHA TALC CT P** acts as functional industrial mineral in paints by creation of bridges between the polymeric binder molecules. The application of this material increase the mud cracking resistance and the physical stability of paint film during and after drying.

Mineralogical composition

Talc:	~ 95 %
Magnesite / Dolomite / Chlorit	< 3 %
Accessory minerals	~ 2 %
Loss of ignition (LOI _{1000 °C})	6 %

Chemical and Physical Data

Product	D50 [µm]	Sieve residue [%]	Whiteness Ry	BET
<i>ALPHA TALC CT 8 P</i>	2.8	32 µm < 0.1	96	20
<i>ALPHA TALC CT 30 P</i>	6.0	63 µm < 0.1	95	10
<i>ALPHA TALC CT 45 P</i>	6.0	71 µm < 0.1	95	10


Application examples

Paints:

- Excellent rheological properties
- Low abrasion values

Special coatings:

- Enhanced reinforcing properties
- High filling degree of end-product
- Reduction of shrinkage



V2 / 2020-09-15 / OK

Alpha Calcit Füllstoff Gesellschaft mbH & Co. KG

D-50971 Köln Postfach 50 11 06 Telefon: +49 2236 8914-0 Email: info@alpha-calcit.de
D-50997 Köln Otto-Hahn-Str. 9-11 Telefax: +49 2236 40644 Internet: www.alpha-calcit.de

Die in unseren Informationen und Druckschriften angegebenen Werte sind Durchschnittswerte ohne Rechtsverbindlichkeit.
The data indicated on our data sheets and printed matters represent average values and are not legally binding.

